



PATENT  
ATTORNEY DOCKET NO.: 046601-5052

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE



Commissioner for Patents  
**BOX PATENT APPLICATION**  
Washington, D.C. 20231

**TRANSMITTAL FOR A NEWLY EXECUTED ORIGINAL APPLICATION  
UNDER 37 C.F.R. §1.53(b)**

This is a request for filing a patent application under 37 C.F.R. §1.53(b) for:

Inventor: Yuzuru FUKUDA

For: RECORDING LIQUID FOR INK PRINTERS AND METHOD OF THE  
FOR RECORDING IMAGES

1. This is a new ☒ **Utility** ☐ **Design** ☐ **Plant** patent application.
2. The papers enclosed to obtain a filing date are as follows:  
36 Pages of Specification including  
0 Title Page  
1 Page of Claims  
1 Page of Abstract  
0 Sheets of drawings containing 0 Figures  
☐ The enclosed drawing(s) are photograph(s), and there is also attached a  
PETITION TO ACCEPT PHOTOGRAPH(S) AS DRAWING(S)
3. Combined Declaration and Power of Attorney  
☒ Enclosed and is executed by all inventors.  
☐ Not Enclosed.  
This application is being filed under the provisions of 37 C.F.R. §1.53(f).  
Applicant(s) await notification from the Patent and Trademark Office of the time  
set for filing the Declaration and paying the filing fees.

## 4. Language

☒ English☐ Non-English

This application is being filed in accordance with 37 C.F.R. §1.52(d) and §608.01 of the MPEP. Applicant(s) await notification from the Patent and Trademark Office of the time set for filing the verified English translation and the processing fee.

## 5. Assignment

☒ An assignment of the invention to Fuji Xerox Co., Ltd. and a PTO Form-1595, Recordation Form Cover Sheet, are enclosed.

☐ An assignment will be filed at a later date.

## 6. Priority - foreign applications under 35 U.S.C. §119(a)-(d) or §365(b) or PCT international applications under 35 U.S.C. §365(a) designating at least one country other than the U.S.

☒ Priority of the following foreign application is claimed:

Country	Application No.	Filed
Japan	11-256916	September 10, 1999

Certified copy: ☐ is/are attached. ☒ will follow.

## 7. Priority based on provisional application(s) - 35 U.S.C. §119(e)

☐ Priority of the following provisional application(s) is claimed:

Application No.	Filed

A. Relate Back - 35 U.S.C. §119(e)

☐ Amend the specification by inserting before the first line the sentence:  
"This application claims priority of copending provisional application(s)  
No. \_\_\_\_\_ filed on \_\_\_\_\_."

8. Small entity status

☐ A statement claiming small entity status under 37 C.F.R. §§1.9 and 1.27 is enclosed.

9. Fee Calculation (37 C.F.R. §1.16)

CLAIMS FOR FEE CALCULATION				
	Number Filed	Number Extra	at Rate of	Basic Fee Utility \$690.00 Design \$310.00
Total Claims (37 C.F.R. §1.16(c))	2 - 20 =	0	\$ 18.00 each=	\$0.00
Independent Claims (37 C.F.R. §1.16(b))	1 - 3 =	0	\$ 78.00 each=	\$0.00
Multiple dependent claim(s), if any (37 C.F.R. §1.16(d))			\$260.00	+
SUB-TOTAL =				\$690.00
Reduction by 1/2 for filing by a small entity				- \$
TOTAL FILING FEE =				\$690.00

10. Fee Payment

☐ Not Enclosed. **NO FEE IS BEING PAID BY CHECK OR DEPOSIT ACCOUNT AT THIS TIME.**

This application is being filed under the provisions of 37 C.F.R. §1.53(f). Applicant(s) await notification from the Patent and Trademark Office of the time set for filing the Declaration and paying the filing fees.

[X] Enclosed.


Two checks in the amounts of \$ 690.00 and \$40.00 representing the basic filing fee of \$690.00 and an assignment recording fee of \$40.00 are enclosed.

11. [X] **Except** for issue fees payable under 37 C.F.R. §1.18, the Commissioner is hereby authorized by this paper to charge any additional fees during the entire pendency of this application including fees due under 37 C.F.R. §§1.16 and 1.17 which may be required, including any required extension of time fees, or credit any overpayment to Deposit Account 50-0310. This paragraph is intended to be a **CONSTRUCTIVE PETITION FOR EXTENSION OF TIME** in accordance with 37 C.F.R. §1.136(a)(3).
12. Additional papers enclosed:
- ☐ Preliminary Amendment
  - ☒ Information Disclosure Statement
  - ☒ Form PTO-1449, 9 documents included
  - ☐ Declaration of Biological Deposit
  - ☐ Submission of "Sequence Listing", computer readable copy and/or amendment pertaining thereto for biotechnology invention containing nucleotide and/or amino acid sequence.

**Please accord this application an application number and filing date.**

Respectfully submitted,

**MORGAN, LEWIS & BOCKIUS LLP**

  
\_\_\_\_\_  
J. Michael Thesz  
Reg. No. 40,354

Dated: June 26, 2000

**Customer No. 009629**  
**MORGAN, LEWIS & BOCKIUS LLP**  
1800 M Street, N.W.  
Washington, D.C. 20036  
(202) 467-7000

# RECORDING LIQUID FOR INK PRINTERS AND METHOD FOR RECORDING IMAGES

## BACKGROUND OF THE INVENTION

### Field of the Invention

The present invention relates to a recording liquid for ink printers and a method for recording images, and in particular relates to a recording liquid for ink printers.

### Discussion of the related Art

As an output device of low running costs and of easy color printing for information equipment such as computers, ink printer systems are attracting public attention. Such systems include an ink-jet system, which is a method of image recording for recording images on recording media such as paper by discharging droplets of a recording liquid from a head, or an acoustic ink printing system as disclosed in Japanese Patent Publication No. 6-102378 (1994). Heretofore, as a recording liquid for ink-jet printers, an aqueous solution of a dye mainly containing water and a dye has been used. However, such a solution has problems in that when the recording liquid discharged from the nozzle arrives at a recording paper, the solution bleeds on the recording paper and produces dots significantly larger than the droplets of the recording liquid formed when discharged from the nozzle, resulting in the low density of recorded images, and the low image quality. Also, since the water resistance of recorded

In order to solve these problems of dye aqueous solutions, recording liquids for ink-jet printers that contain film forming resin particles have been disclosed. For example, a recording liquid containing latex as resin particles is disclosed in Japanese Patent Publication No. 60-32663 (1985); a recording liquid that contains a resin having carboxyl groups and nonionic hydrophilic groups dispersed in water is disclosed in Japanese Patent Laid-Open No. 5-239392 (1993); a recording liquid that contains vinyl polymers with a non-cross-linking structure is disclosed in Japanese Patent Laid-Open No. 5-255628 (1993); and a recording liquid that contains polyester particles having ionic groups is disclosed in Japanese Patent Laid-Open No. 6-340835 (1994). Also, a process of compounding fine particles of a resin such as polyester, and a cross-linking agent, and cross-linking the resin on a recording medium is disclosed in Japanese Patent Publication No. 7-47355 (1995); and a process that uses water-soluble dyes and ultraviolet rays is disclosed in Japanese Patent Laid-Open No. 10-305570 (1998). Furthermore, the inventors of the present invention disclosed a recording liquid that contains pigments and fine particles of two or more resins in Japanese Patent Laid-Open Nos. 10-88045 (1998) and 10-88056 (1998) and in US Patent Application No.

08/925,391 that will be issued soon. (US Patent Appl: NO. 08/925,391 that will be issued soon)

However, any of the recording liquids disclosed in above-mentioned Japanese Patent Publication No. 60-32663 (1985), Japanese Patent Laid-Open Nos. 5-239392 (1993), 5-255628 (1993), and 6-340835 (1994), and Japanese Patent Publication No. 7-47355 (1995) starts to form a film of the fine particles of resins following evaporation of moisture in the recording liquid due to contact with air at the discharging nozzle of the recording head and clogs at the discharging nozzles so that it cannot be discharged from the nozzles stably. Also, the bleeding of the recording liquid due to the capillary action into the fibers of recording paper cannot be completely prevented, and high-quality images cannot be obtained. Furthermore, the permeation of the recording liquid into recording paper cannot be completely prevented, and these recording liquids have limitation in the formation of high-density, high-quality images. Similarly, there is limitation in water resistance. When the above-disclosed recording liquid is diluted by water to prevent clogging at a discharging nozzle, the content of resin particles contained in the same volume of the droplets of the recording liquid, that is, the resin solid content contributing to image formation, decreases, resulting in significant lowering of image density, and high-quality images cannot be obtained. By the use of the above-disclosed conventional recording liquids, an increase in image density

to achieve high-quality images by increasing the content of resin particles is incompatible with the prevention of discharging nozzle clogging. Although a process that uses water-soluble ultraviolet-sensitive dyes, and radiates light (ultraviolet rays) onto the dyes to make them insoluble and fix them is disclosed in Japanese Patent Laid-Open No. 10-305570 (1998), the water resistance and light resistance of the images are not satisfactory because of the use of dyes. Furthermore, since light is irradiated onto colorants, i.e. dyes themselves, the color images are easily changed by aging due to natural exposure to sunlight or the like. Although an increase in image density to achieve high-quality images by increasing the content of resin particles (increase in resin solid content) is compatible with the prevention of discharging nozzle clogging by the use of recording liquids disclosed in Japanese Patent Laid-Open Nos. 10-88045 (1998) and 10-88056 (1998), the stability of discharging must be improved when a large number of sheets are printed using a practically used ink printer.

The present invention has been made in view of the above circumstances and provides a recording liquid for ink printers that can obtain water-resistant high-quality images with high image density, and may not bleed on nor permeate into recording paper, and can be discharged continuously and stably almost without nozzle clogging. The present invention also provides a method for recording images by the use of such a recording liquid.



#### SUMMARY OF THE INVENTION

The recording liquid that achieves the above and other aspects contains a colorant, water, a fine particle of non-photo-curable resin, and a fine particle of photo-curable resins.

Also, the present invention is characterized in that the above-described recording liquid is used in the method for recording images by discharging the droplets of the recording liquid from a recording head to record images on recording media. In this method for image recording, plain paper can be used as a recording medium.

According to the present invention, the achievement of high-density images can be compatible with the prevention of clogging discharging nozzles or apertures, by containing at least two resins, fine particles of non-photo-curable resin(s) and photo-curable resin(s) in the recording liquid.

This would be achieved for the following reasons. Since a light-curable resin does not cure unless it is irradiated by light, film formation at the nozzles of the recording head caused by curing reactions will not occur if the irradiation of the nozzles is prevented. Therefore, the occurrence of clogging is inhibited. If all the resins in the recording liquid are such photo-curable resins, a great deal of light energy and curing time is required for forming films on paper, and thus forming images. However, since both photo-curable resins and non-photo-curable resins are used in the present

invention, the prevention of clogging at the discharging nozzles of the recording head can be compatible with the rapid formation of images.

These photo-curable resins may be either water-soluble resins or aqueous emulsion. In a case of aqueous emulsion the resin is present in the recording liquid in the form of fine particles of resin. If the recording liquid contains the fine particles of two or more different resins, the probability that the fine particles of the same type of resins are present around a certain type of resin particles (the nearest coordinating site) decreases. By this the probability of approaching and collision of the particles of the same type of resins with each other decreases, and a series of processes from the approaching to collision, fusion, and to film formation are inhibited (coordination effect), thereby clogging is prevented. Also, since inter-particle attraction is more difficult to act when the fine particles of different types of resins are present in the recording liquid than the fine particles of the same type of resins are present (repulsive force is easier to act), the approaching of resin particles is prevented, and the probability of collision between resin particles decreases (the inter-particle repulsive force effect), thereby a series of processes from the approaching to collision, fusion, and to film formation are inhibited, and clogging is prevented as in the above-described case. Furthermore, it is considered that the difference in diameters and shapes of particles

between the fine particles of different resins is larger than the difference in diameters and shapes of particles between the fine particles of the same type of resins. When different types of resin particle having different diameters and shapes are present around a certain resin particle, the approaching of the same or different types of resin particles are more difficult than when only resin particles of almost the same diameter and shape are present (the geometrical structure effect), and clogging is prevented similarly to the above. Since the approaching of resin particles to each other is greatly inhibited by the total effect of the above, the total content of resin particles contained in the recording liquid can be increased, and the content of resin particles in a droplet can in turn be increased, enabling images of high image density to be formed.

When the photo-curable resin is water-soluble, the resin dissolves in the recording liquid, and if the content of this resin is made the same as the resin content in the recording liquid when the photo-curable resin is in an aqueous emulsion, the dissolved photo-curable resin can decrease the number of resin particles contained in the recording liquid while maintaining high density of the images, lowers the probability of collision, and prevents clogging even by one type of resin. Also, since the fine particles of the dissolved photo-curable resin enter between the fine particles of the non-photo-curable resin, preventing the approaching of resin particles, clogging can be prevented.

Furthermore, any colorants can be used such as pigments and dyes. However, pigments are more advantageous in light resistance because absorbed light energy can be relieved by crystal-lattice oscillation.

### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

The recording liquid according to the present invention contains colorants, water, and fine particles of non-photo-curable resins and photo-curable resins.

Non-photo-curable resins mean resins that have no mechanisms in their structures to start or promote the curing reaction caused by the irradiation of ultraviolet rays, visible lights, electron beams, and the like. Photo-curable

resins mean resins that have mechanisms to start or promote the curing reaction caused by the irradiation of light (including electromagnetic waves), such as electron beams. Since it is mechanically easy to provide the printer with a radiation source, the photo-curable resins are preferably ultraviolet-curable resins or visible-light-curable resins.

2-ethylhexyl methacrylate, vinyl acetate, acrylonitrile, methyl acrylate, ethyl acrylate, n-butyl acrylate, 2-ethylhexyl acrylate, methacrylic acid, acrylic acid, 2-hydroxyethyl methacrylate, hydroxypropyl methacrylate, 2-hydroxyethyl acrylate, acrylic amide, N-methylol acrylic amide, or glycidyl methacrylate as the monomer.

The fine particles of a non-cross-linking resin and the fine particles of a non-self-cross-linking resin include fine particles of a fluororesin, fine particles of an acrylic resin, fine particles of a polyester resin, fine particles of a vinyl acetate resin, fine particles of a vinyl chloride resin, fine particles of a styrene-butadiene copolymer resin, fine particles of a polyurethane resin, fine particles of a polystyrene resin, fine particles of a vinyl acetate-acrylic copolymer resin, fine particles of a vinyl acetate-acrylic amide copolymer resin, fine particles of an ethylene-vinyl acetate copolymer resin, fine particles of an epoxy resin, fine particles of a polyamide resin, or fine particles of a silicone resin. As the fine particles of a fluororesin among the above, the fine particles of a fluororesin that has fluoro-olefine units is particularly useful. More specifically, the fine particles of a fluorine-containing vinyl ether resin composed of fluoro-olefine units and vinyl ether units can be used effectively. The fluoro-olefine unit used herein is a moiety selected from  $-\text{CF}_2\text{CF}_2-$ ,  $-\text{CF}_2\text{CF}(\text{CF}_3)-$ , and  $-\text{CF}_2\text{CFCl}-$ . The vinyl ether units include  $-\text{CH}_2\text{CH}(\text{OCH}_3)-$ ,  $-\text{CH}_2\text{CH}(\text{OC}_2\text{H}_5)-$ ,  $-\text{CH}_2\text{CH}(\text{OC}_3\text{H}_7)-$ ,  $-\text{CH}_2\text{CH}(\text{OC}_4\text{H}_9)-$ ,  $-\text{CH}_2\text{CH}(\text{OC}_5\text{H}_{11})-$ ,

As the type of copolymers, an alternate copolymer in which fluoro-olefine units and vinyl ether units are completely alternately combined is preferred.

Although the fine particles of non-photo-curable resins contained in the recording liquid of the present invention may be of one type or the combination of two or more resins, the combination of two or more resins is preferable, and the combination of three or more resins is more preferable. Although there is no upper limit in the number of types of resins contained in the recording liquid, if each resin particle is assumed to have the same shape and size, and is assumed to be spherical, the number of particles equidistantly present around a certain particle when the particles are most closely packed, known as the number of closest particles (coordination number), that is the number of particles present in contact with a certain particle is 12. Therefore, the optimal upper limit of the types of resins in the resin particles is considered to be 12. Furthermore,

considering the width of probable oscillation, the upper limit of the types of resins in the resin particles is preferably 18 (12 plus 6). Therefore, the total number is preferably 2 or more and 18 or less, more preferably 3 or more and 12 or less from the point of view of the reduction of probability of approaching and collision between the same type of resin particles due to the coordination effect. The clogging prevention effect becomes more significant when three or more types of resins are used. In the present invention, even if the monomer that constitutes the resin is the same, resins that impart different properties of the dispersion of resin particles due to difference in the way of modification or the like, i.e. at least one of the lowest film forming temperature, glass transition point, ionicity, pH, of weight average molecular weight, may be considered to be of different types.

Although the fine particles of any two or more non-photo-curable resins may be combined, it is preferable that the resin particles contain at least one self-cross-linking resin. It is further preferable that the resin particles contain a combination of fine particles of self-cross-linking resin(s) and non-cross-linking resin(s), from the point of view of producing timewise and structural difference in a process for film formation by each resin to make film forming difficult, thereby preventing clogging, that is, film formation at the discharging portion of the recording head.



When the recording liquid contains two types of fine particles of non-photo-curable resins that contain fine particles of self-cross-linking resin, the content of the fine particles of the self-cross-linking resin in the non-photo-curable resins is preferably in the range between 90 and 5% by weight. Furthermore, when the recording liquid contains n (n: an integer of 3 or more) types or more of the fine particles of non-photo-curable resins, the proportion of fine particles of each resin contained in the non-photo-curable resins is preferably within the range between  $2/n$  and  $0.1/n\%$  by weight, and more preferably within the range between  $2/n$  and  $0.4/n\%$  by weight particularly for the fine particles of the self-cross-linking resin, although it can be suitably selected to realize desired properties to the largest extent.

The average particle diameter of each resin particle used in the present invention is preferably  $0.01\ \mu\text{m}$  or more and  $5\ \mu\text{m}$  or less, more preferably  $0.05\ \mu\text{m}$  or more and  $3\ \mu\text{m}$  or less. If the average particle diameter of each resin particle is less than  $0.01\ \mu\text{m}$ , film-forming properties become poor, and if the average particle diameter of each resin particle is more than  $5\ \mu\text{m}$ , the optical density (image density) will lower.

Photo-curable resins contained in the recording liquid of the present invention may be ultraviolet-curable resins or visible-light-curable resins. Specifically these resins include water-soluble resins and aqueous emulsions. The

water-soluble resins include urethane-acrylate-based resins having alkali metal sulfonate groups, urethane-acrylate-based resins having organic amine carbonate groups, epoxy acrylate-based resins containing carboxyl groups, epoxy (meth)acrylate-based resins having quaternary ammonium salt groups, and polyoxymethylene acrylate/hydrophilic vinyl monomer-based resins. Aqueous emulsions include polyurethane-based resins containing photo-polymerizing acrylate groups on side chains, unsaturated resins containing self-emulsifying carboxyl groups naturally emulsified without using an emulsifier, and forced-emulsifying (meth)acrylate copolymer-based resins emulsified using an emulsifier.

These water-soluble resins and aqueous emulsions may be used separately or may be used together.

In the present invention, the total solid content of fine particles of the non-photo-curable resin and the photo-curable resin, for obtaining satisfactory optical density of the image and discharging stability is preferably within the range between 5 and 95% by weight, more preferably within the range between 15 and 90% by weight, further preferably within the range between 20 and 80% by weight, relative to the total quantity of the recording liquid.

Furthermore, the content of the photo-curable resin relative to the total weight of the non-photo-curable resin and the photo-curable resin is preferably 10-90% by weight, more preferably 20-80% by weight.

Any colorants can be used in the present invention as long as they have good affinity to water which is the main solvent, and can be dispersed evenly. Specifically, pigments, water-soluble dyes, or dispersed dyes can be used.

Pigments that can be used in the present invention include organic pigments, inorganic pigments, and the like. For example, carbon black (C.I. Pigment Black 7) such as furnace black and channel black, or organic pigment such as aniline black (C.I. Pigment Black 1) can be used for black-and-white applications. Pigments for color applications include C.I. Pigment Yellow 1, 3, 12, 13, 14, 17, 24, 34, 35, 37, 42, 53, 55, 81, 83, 95, 97, 98, 100, 101, 104, 108, 109, 110, 117, 120, 138, and 153, C.I. Pigment Violet 1, 3, 5:1, 16, 19, 23, and 38, C.I. Pigment Blue 1, 2, 15, 15:1, 15:2, 15:3, 15:4, 15:6, and 16. The content of pigments contained in the recording liquid is preferably 1-50% by weight, more preferably 1.5-40% by weight. In order to disperse these pigments in water, ultrasonic waves or a ball mill may be used case by case for dispersing. In addition, the pigments may be added to the recording liquid in the form of aqueous pigment dispersion.

The water-soluble dyes that can be used in the present invention include direct dyes and acid dyes. For example, C.I. Direct Black 9, 17, 19, 22, 32, 51, 56, 62, 69, 77, 80, 91, 94, 97, 108, 112, 113, 114, 117, 118, 121, 122, 125, 132, 146, 154, 166, 168, 173, and 199; C.I. Direct Violet 7, 9, 47, 48, 51, 66, 90, 93, 94, 95, 98, 100, and 101; C.I. Direct

Yellow 8, 9, 11, 12, 27, 28, 29, 33, 35, 39, 41, 44, 50, 53, 58, 59, 68, 86, 87, 93, 95, 96, 98, 100, 106, 108, 109, 110, 130, 132, 144, 161, and 163; C.I. Direct Blue 1, 10, 15, 22, 25, 55, 67, 68, 71, 76, 77, 78, 80, 84, 86, 87, 90, 98, 106, 201, 202, 244, 251, and 280; C.I. Acid Black 7, 24, 29, and 48; C.I. Acid Violet 5, 34, 43, 47, 48, 90, and 103; C.I. Acid Yellow 17, 19, 23, 25, 39, 40, 44, 49, 50, 61, 110, 174, and 218; and C.I. Acid Blue 9, 25, 40, 41, 62, 72, 76, 80, 106, 112, 120, 205, 230, 271, and 280 are included, but the water-soluble dyes are not limited to these dyes. The content of these dyes contained in the recording liquid is determined depending on the type of the dye, the type of solvent components, or properties required for the recording liquid, and is generally 0.2-45% by weight, preferably 0.5-30% by weight. Dyes may be added in the recording liquid in the form of an aqueous solution.

Water used in the present invention is preferably ion-exchanged water, ultra-pure water, distilled water, ultra-filtered water, and the like.

In addition to the above, a pH-adjusting agent such as potassium dihydrogen phosphate and sodium dihydrogen phosphate, or a fungicide, an antiseptic agent, or anticorrosive agent such as benzoic acid, dichlophenene, hexachlorophene, and sorbic acid may be added to the recording liquid as required.

Furthermore, various common additives such as a moistening agent, e.g. diethylene glycol, ethylene glycol and glycerin may be added to the recording liquid as required.

The recording liquid of the present invention can be used in a method for image recording that records images on a recording medium such as paper (e.g. plain paper) by discharging the droplets of the recording liquid from a head. In this method of image recording, it is preferable that the recording medium is irradiated by light such as ultraviolet rays and visible light. In this time, the recording head (or the aperture) must not be irradiated.

Also the recording liquid of the present invention can be used suitably not only in ink printers such as ink-jet printers and acoustic ink printers, but also in image recording by the electrostatic suction system.

The present invention will be described below based on the preferred embodiments.

(Example 1)

A recording liquid was prepared by mixing evenly while stirring 35 parts by weight of an aqueous dispersion of dimethylquinacridone pigment (Pigment Red-122) (solid content: 31%, Dainichiseika Color & Chemicals Mfg. Co., Ltd., trade name: EP-1000); 27 parts by weight of an aqueous dispersion containing water and fine particles of acrylic silicone resin (average particle diameter: 0.1 - 0.2  $\mu$ m) having methoxysilyl groups (solid content: 31%, Sanyo Chemical Industries, Ltd., trade name: SW-131); 17 parts by

weight of a resin dispersion containing water and the fine particles of a fluorine-containing vinyl ether-based resin (average particle diameter:  $0.15\text{ }\mu\text{m}$ ) prepared by the emulsion polymerization of fluoro-olefine and vinyl ether (solid content: 50%, Asahi Glass Co., LTD., trade name: FE-3000); and 21 parts by weight of an aqueous emulsion of an ultraviolet-curable urethane acrylate-based resin (solid content: 40%, from Taisei Kako Co., Ltd., tradename: WBR-829). This mixture was filtered by a membrane filter with a pore diameter of  $10\text{ }\mu\text{m}$  to remove coarse particles, to obtain a recording liquid of a pigment (colorant) content in the recording liquid (solid content of pigments  $\times 100/\text{total quantity of the recording liquid}$ ) of 11% by weight, a pigment (colorant) content in the solid component (solid content of pigments  $\times 100/(\text{solid content of pigments} + \text{solid content of resin particles})$ ) of 30% by weight, and a total solid content of resin particles in the recording liquid (total solid content of resin particles  $\times 100/\text{total quantity of the recording liquid}$ ) of 25% by weight.

The recording liquid thus prepared was applied to plain paper for copying machines by the use of a bar coater and dried at room temperature, to form a solid image on the plain paper. The optical density of the obtained image was measured from the surface side on which the image had been formed. As a result, the optical density of the solid image produced by the application of a quantity of the recording liquid as small as  $0.9\text{ mg per }1\text{ cm}^2$  of the image area was as high as 1.6. The

observation of the vertical cross-section of this solid image on the plain paper with an optical microscope revealed that the solid image was mainly formed on the surface of the plain paper, and practically no recording liquid permeated into the plain paper.

On the other hand, the clogging of the discharging nozzles of the recording head by the recording liquid was evaluated as follows. A standard injection needle of an inner diameter of 420  $\mu\text{m}$  (from Iwashita Engineering Co., Ltd.) was set on the tip of a syringe of an inner diameter of 15 mm, and 10 ml of the recording liquid was sucked in this syringe. Next, the upper portion of the syringe was sealed to stop the recording liquid dropping from the syringe and allowed the syringe to stand. After a specified time has passed, the upper portion was opened, and whether the recording liquid could drop continuously from the needle was checked. This operation was repeated by gradually increasing the time, and the longest time when the recording liquid could drop from the needle was recorded as the time until the occurrence of clogging. The thus measured time until the occurrence of clogging by the recording liquid by this method was as long as 240 seconds.

Next, a printing test of this recording liquid on plain paper was carried out using a commercially available ink-jet printer. As a result, the stock solution of this recording liquid could be discharged stably. By the observation of thus printed dots using a magnifier and an

optical microscope, slight blotting was found around the dots, but it did not arise problems in practical uses.

Next, the printing test of this recording liquid on plain paper was carried out using an ultraviolet lamp mounted on a commercially available ink-jet printer, while radiating ultraviolet rays of an intensity of  $100 \text{ mJ/cm}^2$  onto the surface of paper. As a result, the stock solution of this recording liquid could be discharged stably. By the observation of thus printed dots using a magnifier and an optical microscope, clear dots without blotting around the dots was found.

Furthermore, the water resistance was evaluated by spilling water on the solid image formed with the above bar coater and the print sample formed with the printer. The result showed that there were no blotting of the image or spreading of the colorants caused by water, and that the recording liquid of the present invention has a high water resistance.

(Example 2)

Another recording liquid was prepared by mixing evenly while stirring 29 parts by weight of an aqueous dispersion of copper-phthalocyanine pigment (Pigment Blue 15:3) (solid content: 35%, from Dainichiseika Color & Chemicals Mfg. Co., Ltd., trade name: EP-700); 25 parts by weight of a resin dispersion containing water and fine particles of acrylic silicone resin having methoxysilyl groups (average particle diameter:  $0.1 - 0.2 \mu\text{m}$ ) (solid content: 31%, from Sanyo Chemical Industries, Ltd., trade name: SW-131); 26 parts by



weight of a resin dispersion containing water and fine particles of a modified polyester resin having carboxyl groups added on the side chains (average particle diameter: 0.1-0.2  $\mu\text{m}$ ) (solid content: 30%, from Takamatsu Oil and Fat Co., LTD., trade name: A-215G); and 20 parts by weight of an aqueous emulsion of an ultraviolet-curable urethane acrylate-based resin (solid content: 40%, Taisei Kako Co., Ltd., trade name: WBR-829). This mixture was filtered by a membrane filter with a pore diameter of 10  $\mu\text{m}$  to remove coarse particles, to obtain a recording liquid of a pigment (colorant) content in the recording liquid of 10% by weight, a pigment (colorant) content in the solid component of 30% by weight, and a total solid content of resin particles in the recording liquid of 24% by weight.

The recording liquid thus prepared was applied to plain paper for copying machines by the use of a bar coater and dried at room temperature, to form a solid image on the plain paper. The optical density of the obtained image was measured from the surface side on which the image had been formed. As a result, the optical density of the solid image produced by the application of a quantity of the recording liquid as small as 0.9 mg per 1  $\text{cm}^2$  of the image area was as high as 1.5. The observation of the vertical cross-section of this solid image on the plain paper with an optical microscope revealed that the solid image was mainly formed on the surface of the plain paper, and practically no recording liquid permeated into the plain paper.

Next, the clogging of the discharging nozzles of the recording head by the recording liquid was evaluated by the same way as in Example 1. The thus measured time until the occurrence of clogging by the recording liquid by this method was as long as 250 seconds.

Furthermore, a printing test of this recording liquid on plain paper was carried out using a commercially available ink-jet printer. As a result, the stock solution of this recording liquid could be discharged stably. By the observation of thus printed dots using a magnifier and an optical microscope, slight blotting was found around the dots, but it did not arise problems in practical uses.

Next, the printing test of this recording liquid on plain paper was carried out using an ultraviolet lamp mounted on a commercially available ink-jet printer, while radiating ultraviolet rays of an intensity of  $100 \text{ mJ/cm}^2$  onto the surface of paper. As a result, the stock solution of this recording liquid could be discharged stably. By the observation of thus printed dots using a magnifier and an optical microscope, clear dots without blotting around the dots was found.

Next, the water resistance was evaluated by spilling water on the solid image formed with the above bar coater and the print sample formed with the printer. The result showed that there were no blotting of the image or spreading of the colorants caused by water, and that the recording liquid of the present invention has a high water resistance.

(Example 3)

Another recording liquid was prepared by mixing evenly while stirring 34 parts by weight of an aqueous dispersion of disazo-pigment (Pigment Yellow 12) (solid content: 33%, from Dainichiseika Color & Chemicals Mfg. Co., Ltd., trade name: EP-500); 9 parts by weight of a resin dispersion containing water and fine particles of acrylic silicone resin having methoxysilyl groups (average particle diameter: 0.1-0.2  $\mu\text{m}$ ) (solid content: 31%, from Sanyo Chemical Industries, Ltd., trade name: SW-131); 5 parts by weight of a resin dispersion containing water and fine particles of a fluorine-containing vinyl ether-based resin (average particle diameter: 0.15  $\mu\text{m}$ ) prepared by the emulsion polymerization of fluoro-olefine and vinyl ether (solid content: 50%, from Asahi Glass Co., LTD., trade name: FE-3000); 6 parts by weight of a resin dispersion containing water and fine particles of a modified styrene-butadiene copolymer (average particle diameter: 0.19  $\mu\text{m}$ ) (solid content: 45%, from Sumika ABS Latex, trade name: SN-335); and 46 parts by weight of an aqueous emulsion of an ultraviolet-curable urethane acrylate-based resin (solid content: 40%, from Taisei Kako Co., Ltd., tradename: WBR-829). This mixture was filtered by a membrane filter with a pore diameter of 10  $\mu\text{m}$  to remove coarse particles, to obtain a recording liquid of a pigment (colorant) content in the recording liquid of 11% by weight, a pigment (colorant) content in the solid component of 30% by weight, and a total

solid content of resin particles in the recording liquid of 26% by weight.

The recording liquid containing a large proportion of photo-curable resins thus prepared was applied to plain paper for copying machines by the use of a bar coater and dried at room temperature, to form a solid image on the plain paper. The optical density of the obtained image was measured from the surface side on which the image had been formed. As a result, the optical density of the solid image produced by the application of a quantity of the recording liquid as small as 0.9 mg per 1 cm<sup>2</sup> of the image area was as high as 1.4. The observation of the vertical cross-section of this solid image on the plain paper with an optical microscope revealed that the solid image was mainly formed on the surface of the plain paper, and practically no recording liquid permeated into the plain paper.

Next, the clogging of the discharging nozzles of the recording head by the recording liquid was evaluated by the same way as in Example 1. The thus measured time until the occurrence of clogging by the recording liquid by this method was as long as 320 seconds.

Furthermore, a printing test of this recording liquid on plain paper was carried out using a commercially available ink-jet printer. As a result, the stock solution of this recording liquid could be discharged stably. By the observation of thus printed dots using a magnifier and an

optical microscope, slight blotting was found around the dots, but it did not arise problems in practical uses.

Next, the printing test of this recording liquid on plain paper was carried out using an ultraviolet lamp mounted on a commercially available ink-jet printer, while radiating ultraviolet rays of an intensity of  $100 \text{ mJ/cm}^2$  onto the surface of paper. As a result, the stock solution of this recording liquid could be discharged stably. By the observation of thus printed dots using a magnifier and an optical microscope, clear dots without blotting around the dots was found.

Next, the water resistance was evaluated by spilling water on the solid image formed with the above bar coater and the print sample formed with the printer. The result showed that there were no blotting of the image or spreading of the colorants caused by water, and that the recording liquid of the present invention has a high water resistance.

(Example 4)

Another recording liquid was prepared by mixing evenly while stirring 27 parts by weight of an aqueous dispersion of copper-phthalocyanine pigment (Pigment Blue 15:3) (solid content: 35%, from Dainichiseika Color & Chemicals Mfg. Co., Ltd., trade name: EP-700); 18 parts by weight of a resin dispersion containing water and fine particles of acrylic silicone resin having methoxysilyl groups (average particle diameter:  $0.1\text{-}0.2 \text{ }\mu\text{m}$ ) (solid content: 31%, from Sanyo Chemical Industries, Ltd., trade name: SW-131); 19 parts by weight of a resin dispersion containing water and fine

particles of a modified polyester resin (average particle diameter: 0.1-0.2  $\mu\text{m}$ ) having carboxyl groups added on the side chains (solid content: 30%, from Takamatsu Oil and Fat Co., LTD., trade name: A-215G); 14 parts by weight of an aqueous emulsion of an ultraviolet-curable urethane acrylate-based resin (solid content: 40%, Taisei Kako Co., Ltd., trade name: WBR-829); and 22 parts by weight of an aqueous solution of a polyoxymethylene acrylate/hydrophilic vinyl monomer-based water soluble resin (from Adel Company, trade name: K-40) (solid content: 25%). This mixture was filtered by a membrane filter with a pore diameter of 10  $\mu\text{m}$  to remove coarse particles, to obtain a recording liquid of a pigment (colorant) content in the recording liquid of 9% by weight, a pigment (colorant) content in the solid component of 30% by weight, and a total solid content of resin particles in the recording liquid of 22% by weight.

The recording liquid thus prepared was applied to plain paper for copying machines by the use of a bar coater and dried at room temperature, to form a solid image on the plain paper. The optical density of the obtained image was measured from the surface side on which the image had been formed. As a result, the optical density of the solid image produced by the application of a quantity of the recording liquid as small as 0.9 mg per 1  $\text{cm}^2$  of the image area was as high as 1.4. The observation of the vertical cross-section of this solid image on the plain paper with an optical microscope revealed that the solid image was mainly formed on the surface of the plain

paper, and practically no recording liquid permeated into the plain paper.

Next, the clogging of the discharging nozzles of the recording head by the recording liquid was evaluated by the same way as in Example 1. The thus measured time until the occurrence of clogging by the recording liquid by this method was as long as 260 seconds.

Furthermore, a printing test of this recording liquid on plain paper was carried out using a commercially available ink-jet printer. As a result, the stock solution of this recording liquid could be discharged stably. By the observation of thus printed dots using a magnifier and an optical microscope, slight blotting was found around the dots, but it did not arise problems in practical uses.

Next, the printing test of this recording liquid on plain paper was carried out using an ultraviolet lamp mounted on a commercially available ink-jet printer, while radiating ultraviolet rays of an intensity of  $100 \text{ mJ/cm}^2$  onto the surface of paper. As a result, the stock solution of this recording liquid could be discharged stable. By the observation of thus printed dots using a magnifier and an optical microscope, clear dots without blotting around the dots was found.

Next, the water resistance was evaluated by spilling water on the solid image formed with the above bar coater and the print sample formed with the printer. The result showed that there were no blotting of the image or spreading of the

colorants caused by water, and that the recording liquid of the present invention has a high water resistance.

(Comparative Example 1)

A recording liquid was prepared in the same way as in Example 1 except adding no photo-curable resins, by mixing evenly while stirring 34 parts by weight of an aqueous dispersion of dimethylquinacridone pigment (Pigment Red-122) (solid content: 31%, from Dainichiseika Color & Chemicals Mfg. Co., Ltd., trade name: EP-1000); 40 parts by weight of a resin dispersion containing water and fine particles of acrylic silicone resin having methoxysilyl groups (average particle diameter: 0.1 - 0.2  $\mu\text{m}$ ) (solid content: 31%, Sanyo Chemical Industries, Ltd., trade name: SW-131); and 25 parts by weight of a resin dispersion containing water and fine particles of a fluorine-containing vinyl ether-based resin (average particle diameter: 0.15  $\mu\text{m}$ ) prepared by the emulsion polymerization of fluoro-olefine and vinyl copolymers (solid content: 50%, from Asahi Glass Co., LTD., trade name: FE-3000). This mixture was filtered by a membrane filter with a pore diameter of 10  $\mu\text{m}$  to remove coarse particles, to obtain a recording liquid of a pigment (colorant) content in the recording liquid of 11% by weight, a pigment (colorant) content in the solid component of 30% by weight, and a total solid content of resin particles in the recording liquid of 25% by weight.

For the recording liquid thus prepared, the optical density and time until clogging occurred were measured, and



the printing test on plain paper using a commercially available ink-jet printer was carried out in the same way as in Example 1. As a result, the optical density of the solid image produced by the application of a quantity of the recording liquid as small as 0.9 mg per 1 cm<sup>2</sup> of the image area was 1.7. However, the time until clogging occurred was as short as 80 seconds. As a result of the printing test using a commercially available ink-jet printer, printing was feasible in the initial stage, but with increase in the number of printing, the partial blur of printed characters was found. (Comparative Example 2)

Another recording liquid was prepared in the same way as in Example 2 except adding no photo-curable resins, by mixing evenly while stirring 27 parts by weight of an aqueous dispersion of copper-phthalocyanine pigment (Pigment Blue 15:3) (solid content: 35%, from Dainichiseika Color & Chemicals Mfg. Co., Ltd., trade name: EP-700); 36 parts by weight of a resin dispersion containing water and fine particles of acrylic silicone resin having methoxysilyl groups (average particle diameter: 0.1 - 0.2  $\mu$ m) (solid content: 31%, from Sanyo Chemical Industries, Ltd., trade name: SW-131); and 37 parts by weight of a resin dispersion containing water and fine particles of a modified polyester resin (average particle diameter: 0.1 - 0.2  $\mu$ m) having carboxyl groups added on the side chains (solid content: 30%, from Takamatsu Oil and Fat Co., LTD., trade name: A-215G). This mixture was filtered by a membrane filter with a pore diameter

For the recording liquid thus prepared, the optical density and time until clogging occurred were measured, and the printing test on plain paper using a commercially available ink-jet printer was carried out in the same way as in Example 2. As a result, the optical density of the solid image produced by the application of a quantity of the recording liquid as small as 0.9 mg per 1 cm<sup>2</sup> of the image area was 1.7. However, the time until clogging occurred was as short as 90 seconds. As a result of the printing test using a commercially available ink-jet printer, printing was feasible in the initial stage, but with increase in the number of printing, the partial blur of printed characters was found. (Comparative Example 3)

Another recording liquid was prepared in the same way as in Example 3 except adding no photo-curable resins, by mixing evenly while stirring 34 parts by weight of an aqueous dispersion of disazo-pigment (Pigment Yellow 12) (solid content: 33%, from Dainichiseika Color & Chemicals Mfg. Co., Ltd., trade name: EP-500); 28 parts by weight of a resin dispersion containing water and fine particles of acrylic silicone resin having methoxysilyl groups (average particle diameter: 0.1-0.2  $\mu\text{m}$ ) (solid content: 31%, from Sanjo

Chemical Industries, Ltd., trade name: SW-131); 17 parts by weight of a resin dispersion containing water and fine particles of a fluorine-containing vinyl ether-based resin (average particle diameter:  $0.15\text{ }\mu\text{m}$ ) prepared by the emulsion polymerization of fluoro-olefine and vinyl ether copolymer (solid content: 50%, from Asahi Glass Co., LTD., trade name: FE-3000); and 20 parts by weight of a resin dispersion containing water and fine particles of a modified styrene-butadiene copolymer (average particle diameter:  $0.19\text{ }\mu\text{m}$ ) (solid content: 45%, from Sumika ABS Latex, trade name: SN-335). This mixture was filtered by a membrane filter with a pore diameter of  $10\text{ }\mu\text{m}$  to remove coarse particles, to obtain a recording liquid of a pigment (colorant) content in the recording liquid of 11% by weight, a pigment (colorant) content in the solid component of 30% by weight, and a total solid content of resin particles in the recording liquid of 27% by weight.

For the recording liquid thus prepared, the optical density and time until clogging occurred were measured, and the printing test on plain paper using a commercially available ink-jet printer was carried out in the same way as in Example 3. As a result, the optical density of the solid image produced by the application of a quantity of the recording liquid as small as  $0.9\text{ mg per }1\text{ cm}^2$  of the image area was 1.7. However, the time until clogging occurred was as short as 130 seconds. As a result of the printing test using a commercially available ink-jet printer, printing was

Another recording liquid was prepared in the same way as in Example 1 except adding one more type of non-photo-curable resin in place of a photo-curable resin, by mixing evenly while stirring 36 parts by weight of an aqueous dispersion of dimethyl quinacridone-based pigment (Pigment Red-122) (solid content: 31%, from Dainichiseika Color & Chemicals Mfg. Co., Ltd., trade name: EP-1000); 28 parts by weight of a resin dispersion containing water and fine particles of acrylic silicone resin having methoxysilyl groups (average particle diameter: 0.1-0.2  $\mu\text{m}$ ) (solid content: 31%, from Sanyo Chemical Industries, Ltd., trade name: SW-131); 17 parts by weight of a resin dispersion containing water and fine particles of a fluorine-containing vinyl ether-based resin (average particle diameter: 0.15  $\mu\text{m}$ ) prepared by the emulsion polymerization of fluoro-olefine and vinyl ether (solid content: 50%, from Asahi Glass Co., LTD., trade name: FE-3000); and 19 parts by weight of a resin dispersion containing water and fine particles of a modified styrene-butadiene copolymer (average particle diameter: 0.19  $\mu\text{m}$ ) (solid content: 45%, from Sumika ABS Latex, trade name: SN-335). This mixture was filtered by a membrane filter with a pore diameter of 10  $\mu\text{m}$  to remove coarse particles, to obtain a recording liquid of a pigment (colorant) content in the recording liquid of 11% by weight, a pigment (colorant)

content in the solid component of 30% by weight, and a total solid content of resin particles in the recording liquid of 26% by weight.

For the recording liquid thus prepared, the optical density and time until clogging occurred were measured, and the printing test on plain paper using a commercially available ink-jet printer was carried out in the same way as in Example 1. As a result, the optical density of the solid image produced by the application of a quantity of the recording liquid as small as 0.9 mg per 1 cm<sup>2</sup> of the image area was 1.6. However, the time until clogging occurred was as short as 120 seconds. As a result of the printing test using a commercially available ink-jet printer, printing was feasible in the initial stage, but with increase in the number of printing, the partial blur of printed characters was found.

By the use of the recording liquids of Examples 1-4, as described above, the compatibility of high optical density with the prevention of clogging could be achieved, unlike Comparative Examples.

#### Effects of the Invention

According to the present invention, there is provided a recording liquid that produces high-quality images having a very high image density and water resistance without blotting or permeation on recording paper, and that excels in discharging stability because the recording liquid contains colorants, water, fine particles of a non-photo-curable resin and a photo-curable resin. Also according to

the present invention, a method for recording images that have the above-described advantages.

WHAT IS CLAIMED IS:

1. A recording liquid for ink printers comprising a colorant, water, and a fine particle of non-photo-curable resin and a fine particle of photo-curable resin.
2. A method for recording images on a recording medium by discharging the droplets of the recording liquid from a recording head, wherein the recording liquid according to claim 1 is used as the recording liquid.

## ABSTRACT

There are provided a recording liquid that produces high-quality images having a very high image density and water resistance without blotting or permeating into recording paper, and excels in discharging properties; and a method for recording images by the use of such a solution. The recording liquid for ink printers according to the present invention contains a colorant, water, and a fine particle of non-photo-curable resin and a fine particle of photo-curable resin. The method for recording images on a recording medium has the step of discharging the droplets of the recording liquid from a recording head, wherein the above recording liquid is used as the recording liquid.



# APPLICATION FOR UNITED STATES PATENT DECLARATION AND POWER OF ATTORNEY

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name; that

I verily believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural inventors are named below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

RECORDING LIQUID FOR INK PRINTERS AND METHOD FOR RECORDING IMAGES

described and claimed in the specification:

Check one

- \*a. ☒ attached hereto.  
b. ☐ filed on \_\_\_\_\_ as Application Serial No. \_\_\_\_\_ and amended on \_\_\_\_\_ (if applicable)

I hereby state that I have reviewed and understand the contents of the above-identified application, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose to the Office all information known to me to be material to patentability as defined in Title 37, Code of Federal Regulations, § 1.56.

Under Title 35 U.S. Code § 119, the priority benefits of the following foreign application(s) and/or United States provisional application(s) filed within one year prior to this application are hereby claimed:

Japanese Patent Application No. 11-256916, filed on September 10, 1999

The following application(s) for patent or inventor's certificate on this invention were filed in countries foreign to the United States of America either (a) more than one year prior to this application, or (b) before the filing date of the above-named foreign priority application(s) and/or United States provisional application(s):

As a named inventor, I hereby appoint the registered practitioners of Morgan, Lewis & Bockius LLP included in the Customer Number provided below to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith, and direct that all correspondence be addressed to that Customer Number.

Customer Number: **009629**

I hereby declare that I have reviewed and understand the contents of this Declaration, and that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Typewritten Full Name  
of Sole or First inventor:

Yuzuru		Fukuda	
Given Name	Middle Initial	Family Name	
Yuzuru		Fukuda	
6	8	2000	
Month Day		Year	
Nakai-machi		Japan	
City		Country	
Japan			
c/o Fuji Xerox Co., Ltd., 430, Sakai, Nakai-machi,			
Ashigarakami-gun, Kanagawa, Japan			

\*\*Inventor's Signature:

\*\*Date of Signature:

Residence:

Citizenship:

Post Office Address:  
(Insert complete mailing  
address, including country)

\*This form may be executed only when attached to the specification (including claims) at the end thereof if Box a. is checked.

\*\*Note to Inventor: Please sign name exactly as it appears above and insert the actual date of signing.

IF THERE IS MORE THAN ONE INVENTOR USE PAGE 2 AND PLACE AN "X" HERE ☐